

TG Steels

2738

PRIME

2738HH

PRIME

Prehardened mold steel with good machinability suitable for general applications with good polish ability and texturing

2738 PRIME - 2738HH PRIME;

- are produced by a process that ensures a good level of cleanliness and homogeneity.
- have a good toughness better than 2312 PRIME and they can be also used for mechanical applications.
- has a good polishability, is good for texturing, better than 2312 PRIME.
- can also be welded and exhibits a good machinability but still lower than 2312 PRIME.
- are delivered at a hardness of 300 HB for 2738 PRIME and 350 HB for 2738HH and can be machined without further heat treatment.
- have a very good suitability for surface treatments such as gas, ionic or salt bath nitriding, as well as PVD or CVD coatings.

Applications

2738 PRIME - 2738HH PRIME can be used for small sizes to very large injection molds requiring good polishability and good texturing level.

2738 PRIME - 2738HH PRIME can also be used for molds for abrasive polymers and reinforced plastics with appropriate surface treatment.

2738 PRIME - 2738HH PRIME can be used for all the secondary parts in molding applications and also frames for plastic molds.

2738 PRIME - 2738HH PRIME can also be used for mechanical applications requiring a hardness

around 300 HB resp. 350 HB associated with a good toughness.

2738 PRIME - 2738HH PRIME can also be used for pressure casting dies, recipient sleeves.

Main properties

- Prehardened steel at 300 HB resp. 350 HB ready to be machined without any further heat treatment
- Good polishability and good texturing
- Good toughness
- Good machinability
- Suitable for surface treatments

Designation

Werkstoff Nr	ISO	China GB	JIS Japan	UK	AISI USA	Russia Gost	AFNOR	Other / Special
1.2738	40CrMnNiMo8-6-4	3Cr2MnNiMo	HPM1	-	≈P20+Ni	-	40CMND8	-

Chemical composition (typical)

C	Mn	Si	P	S	Cr	Ni	Mo
0.40	1.45	0.30	< 0.035	< 0.035	1.95	1.10	0.20

Structure

The structure of the 2738 PRIME - 2738HH PRIME is fine and homogeneous without precipitation or alignments of carbides. The heat treatment (*quench and tempering*) is optimized for high homogeneity of hardness from surface to core even for thicker blocks.

Hardness at the time of delivery

2738 PRIME: heat treated for 290 - 325 HB

2738 HH PRIME: heat treated for 325 - 355 HB

Typical mechanical properties in hardened conditions (*results from internal tests not indicated on the certificates*)

MPa	TS MPa	YS 0.2% MPa	Elongation %	KU J à 20°C
2738 PRIME	1000	875	16	30
2738 HH PRIME	1100	950	14	22

Physical properties

Temperature	20°C	100°C	200°C	300°C
Volumic mass kg/m ³	7825	7815	7780	7765
Young Modulus N/mm ²	212000	209000	207000	192000
Thermal conductivity W/m.K	34	35.0	35.5	34.7
Coefficient of linear expansion 10 ⁻⁶ /K	11.1	12.0	13.0	13.4

Heat treatment

The 2738 PRIME - 2738HH PRIME are delivered heat treated at 290 - 325 HB resp. 325 - 355 HB and there is no need for further heat treatment.

In case of need (e.g. if other mechanical properties are required) the following parameters can be used.

SOFT ANNEALING

Temperature: 710 - 730°C, duration 1h + 1h for 25 mm thickness. slow cooling in the furnace (10 to 20°C/h). The atmosphere in the furnace must be reducing to avoid decarburization of the steel.

STRESS RELIEVING

After machining, it is recommended to perform stress relieving at 550°C maximum for a minimum of 2 hours, followed by slow cooling in the furnace to 450°C.

AUSTENITIZATION

In order to avoid any risk of cracking it is recommended to preheat in 2 steps.

- **1st preheating step:**
temperature: 450°C time: 30 s/mm of thickness
- **2nd preheating step:**
temperature: 650°C time: 30 s/mm of thickness

Recommended austenitizing temperature: 850 - 870°C. The holding time should not be too long to avoid a risk of grain coarsening and a loss of toughness. It is recommended to keep the part at the austenitizing temperature 30 minutes per inch of thickness as soon as the temperature of the surface reach the austenitization temperature.

QUENCHING MEDIUM


Oil at 80°C, vacuum (pressure > 6 bars), salt bath 500 - 550°C.

To ensure good toughness, treatment with oil or salt bath is preferable.

TEMPERING

To ensure a minimum residual austenite rate as well as greater tool stability, it is essential to perform a double tempering. Each tempering is followed by a cooling under 100°C.

Each tempering time must be at least equal to 1h + 1h for 25 mm of thickness of the treated part (equivalent thermal thickness).



Surface treatment

NITRIDING

2738 PRIME - 2738HH PRIME can be nitrided at temperatures less than or equal to 20°C below tempering temperatures without risk of deterioration of the mechanical characteristics. With a gas nitriding at 520°C (25 h) the surface hardness is 750 - 800 HV1 with a diffusion layer of 0.2 mm.

PVD, CVD

2738 PRIME - 2738HH PRIME are suitable for all kinds of PVD and CVD treatment as soon as the treatment temperature is 30°C lower than the last tempering temperature.

Polishing

2738 PRIME - 2738HH PRIME are perfectly suitable for polishing in the treated state and can be used for applications requiring a sufficient level of polish for transparent parts ($R_t \leq 5 \mu\text{m}$, CNOMO level 1.5, Rugotest N5).

Optimal polishing is achieved by performing consecutive steps with similar roughness and stopping each step as soon as the last scratch from the previous step disappears.

Texturing

2738 PRIME - 2738HH PRIME are suitable for chemical or laser texturing.

Induction or laser hardening

2738 PRIME - 2738HH PRIME can be surface hardened up to 52 - 54 HRC by induction or laser. Please consult us for more details. A stress relieving at 150°C for minimum 2 h is mandatory after surface hardening.

Machining

The machining parameters below are given for information only and must be adapted according to the equipment and usual machining conditions.

TURNING

	Carbide tool	
	Rough machining	Finishing
Cutting speed m/min	120 - 140	140 - 180
Feed mm/r	0.15 - 0.35	0.05 - 0.2
Depth of cut mm	2 - 4	1

MILLING: SURFACING

	Milling with carbide tools		Solid tool
	Rough machining	½ Finishing	Finishing
Cutting speed m/min	100 - 140	140 - 160	50 - 70
Feed mm/r	0.15 - 0.35	0.1 - 0.2	0.005 - 0.15
Depth of cut mm	2 - 4	2	

DRILLING: HSS TWIST DRILL

Drill diameter mm	Cutting speed m/min	Feed mm/t
< 5	14	0.05 - 0.10
5 - 10	14	0.10 - 0.15
10 - 15	14	0.18 - 0.25
15 - 20	14	0.22 - 0.29

DRILLING: CARBIDE DRILL

	Carbide type		
	Indexable insert	Solid carbide	Carbide tip
Cutting speed m/ min	150 - 170	90 - 120	50 - 70
Feed mm/t	0.05 - 0.10	0.10 - 0.25	0.15 - 0.25

FINE GRINDING

General indications for grinding wheels to be used on 2738 PRIME - 2738HH PRIME in the heat treated condition.

Usually, rather soft vitrified aluminum oxide grinding wheels (*grades G for plane grinding to K for cylindrical grinding*) are used.

Particular attention will be paid to effective cooling of the surface during grinding to prevent degradation of the material surface.

ELECTRO-DISCHARGE MACHINING

2738 PRIME - 2738HH PRIME are also suitable for EDM machining (*wire or electrode*). preferably, the machining will be carried out with a low current density and a high frequency in order to limit the thickness of the white layer as much as possible.

Then it is necessary to carry out a stress relieving at 25°C below the last tempering in order to reduce the level of residual stresses (*which could lead to a risk of cracking*) and to carry out a polishing to completely remove the white layer formed during the discharge machining process.

Welding

The 2738 PRIME - 2738HH PRIME could be welded in the heat treated condition.

- **Method:** TIG
- **Feeder wire:** 25CrMo4 or 2738
- **Preheating:** 350°C

Hold at 200°C during the welding operation with a maximum interpass temperature at 350°C. Slow cooling (*max 20°C/h*) after welding.

- **Post treatment:**
 - » At 550°C, duration 1h + 1h for 25 mm of thickness. slow cooling in the furnace (*10 to 20°C/h*).
 - » **Hardness of the welded area:** ≈300 HB.

Depending on the surface (*polished or textured*) the welding conditions can be optimized. Please consult us for more details.



TG Steels

E info@tgsteels.com W www.tgsteels.com

Atlas Special Steels, s.l.
Avinguda de Can Sucarrats, 88-92,
08191 Rubí, Barcelona, Spain
+34 938 233 590
info@atlassteels.eu

Atlas Special Steels Unipessoal, Lda
Rua do Antuã, nr. 64 pavilhão A e B
3720-558 Travanca – OAZ, Portugal
+351 256 245 497
info@atlassteels.eu

Five Star Special Steel Europe srl
Via Glenn Curtiss, 9, 25018
Montichiari BS, Italy
+39 030 524 3724
info@fssseurope.com

GNG Consultoria
Rua Ituporanga, 210 – Bom Retiro
Joinville – SC – 89222-430
+55 47 99669-5557
marcus@gngconsultoria.com.br

OSS Canada Special Steel Inc
2384 Speers Rd, Oakville,
ON, Canada L6L 5M2
905-827-5888
sales@oss-material.ca

OSS Special Steel Inc.
2015 Mitchell Blvd Suite C
Schaumburg, IL 60193
(618) 426 – 6158
sales@oss-material.com

TG Steels s.r.o.
Libušina 850, Dubí 272 03
Kladno, Czech Republic
info@tgsteels.com

TG Middle East
Kocaeli KOBİ OSB, Köselер Mh.,
3. Cd., No: 15 Dilovası, Kocaeli, Türkiye
+90 262 728 11 67 (pbx)
info@tgme.com.tr